Plow Pte. Ltd.
Address: 12 Marina View, #23-01,
Asia Square Tower 2, Singapore (018961)

E-mail: info@plow.group Phone: +65 3157 1213

## **Technical Data Sheet**

### **Product: SBR-1712**

#### Description

The synthetic butadiene-alpha-methylstyrene (styrene) rubber is produced by emulsion copolymerization of butadiene with alpha-methylstyrene (styrene) at low temperatures with an emulsifier. The mixture of VTS-150 and VS-1 is used as an antioxidant. The SBR-1712 is an oil-extended rubber filled with the oil PN-6 (DAE type oil).

#### **Application**

The SBR-1712 is a general-purpose rubber and it is widely used in the tire industry to produce auto-tire casings and to produce various mechanical rubber goods.

#### **Specifications**

Parameter	Value	Test Method
Mooney viscosity MML 1+4 (100°C)	46-58	ASTM D 1646 (7.2.2)
Mooney viscosity lot spread, max	8	-
Mass fraction of volatile matters, %, max.	0,6	ASTM D 5668
Mass fraction of Ash, %, max.	0,6	ASTM D 5667
Mass fraction of organic acids, %	4,0-5,8	- ASTM D 5774
Mass fraction of organic acids soaps, %	0,30	
Mass fraction of solvent extract, %	29 - 35	
Mass fraction of oil	25 - 30	
Mass fraction of second bound monomer, %	22,0 - 25,0	ASTM D 5775
(alphamethylstyrene)		
Vulcanization characteristics (rotorless rheometer of the type MDR-2000 (ASTM D 3185, method A)		
Minimum torque, ML,dNm	1,4 – 3,0	ASTM D 5289
Maximum torque, MH, dNm	12,0 – 18,5	
Vulcanization start time, ts1, min	3,2-6,5	
Time to reach 50% degree of vulcanization, t50, min	6,5 – 10,5	
Time to reach 90% degree of vulcanization, t90, min	12,0 – 18,5	
Elastic and strength properties of rubbers under elongation (in optimum vulcanization)		
Modulus at 300% elongation, MPa, min.	9,8	ASTM D 412
Conditional tensile strength, MPa, min.	18,0	
Relative elongation at break, %, min	380	

#### **Packaging**

Public Joint-Stock Company "Omsky kauchuk"

#### **Packaging**

The SBR-1712 is produced in the form of bales about 30 kg each, wrapped in polyethylene film. Packed in universal plywood containers (UPC). (See appendix)

#### Storage and transportation

Rubber is stored indoors at a temperature not higher than +30 °C. During storage, the rubber must be protected from contamination, direct sunlight, and precipitation.



# **Universal Plywood Container (UPC)**

#### **Characteristics:**

- The plywood box is equipped with a laminated polypropylene fabric cover for cargo safety;
- The box is folding with a removable wall for easy unloading;
- Metal elements ensure container durability;
- The box is assembled manually without the need to use auxiliary materials or tools.

#### Parameters:

Tare Weight: 70 kg (± 5 kg)

Net weight: 1,260 kg (42 briquettes)

Gross Weight: 1,330 kg (42 briquettes)



